

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 9/7/97	3. REPORT TYPE AND DATES COVERED Final 5/20/93-7/7/97		
4. TITLE AND SUBTITLE Semiconductor Heterojunction Engineering		5. FUNDING NUMBERS DAAH04-93-G-0206		
6. AUTHOR(S) Alfonso Franciosi				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Minnesota, Minneapolis, MN 55455		8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211		10. SPONSORING / MONITORING AGENCY REPORT NUMBER ARO 30 771. 26-EL		
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.		12b. DISTRIBUTION CODE 19980521 117		
13. ABSTRACT (Maximum 200 words) Semiconductor interfaces such heterojunctions and metal/semiconductor contacts are crucial components of modern solid state electronic devices ranging from MOSFETs and MODFETs to LEDs and lasers. The possibility of tuning the interface potential barrier to a given device application and optimizing carrier injection or confinement would offer an important new degree of freedom in device design. The focus of our work was the characterization and control of the band alignment in a number of interfaces of current interest for the development of a viable blue optoelectronic technology. These included wide gap II-VI and III-V semiconductor materials fabricated by molecular beam epitaxy (MBE) on GaAs wafers. We have exploited the MBE growth parameter to vary the interface composition and morphology, and examined the resulting variations in the structural and electronic properties of the junctions. Among the major successes of our program was the fabrication of local interface dipoles in the interface region of II-VI/III-V heterojunctions to independently tune band offsets and structural properties, the implementation of metal/ZnSe contacts with unprecedentedly low resistivity, and the development of new substrates lattice-matched to the active layer for the fabrication of II-VI based blue-green lasers.				
14. SUBJECT TERMS Heterojunctions, contacts, II-VI semiconductors		15. NUMBER OF PAGES 8		
		16. PRICE CODE		
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

1. STATEMENT OF THE PROBLEM

Semiconductor interfaces such heterojunctions and metal/semiconductor contacts are crucial components of modern solid state electronic devices ranging from MOSFETs and MODFETs to LEDs and lasers. The possibility of tuning the interface potential barrier to a given device application and optimizing carrier injection or confinement would offer an important new degree of freedom in device design. The focus of our work was the characterization and control of the band alignment in a number of interfaces of current interest for the development of a viable blue optoelectronic technology. These included wide gap II-VI and III-V semiconductor materials fabricated by molecular beam epitaxy (MBE) on GaAs wafers, II-VI/II-VI heterostructure and multiple quantum wells, as well as metal/semiconductor contacts. On the one hand, little was known about the basic properties of such interfaces, and the possibility that the local interface environment might affect the band alignment. On the other hand, the development of a viable blue optoelectronic technology is currently hindered by the insufficient performance of such interfaces, which leads to high dissipation and low device lifetime. We have exploited the MBE growth parameter to vary the interface composition and morphology, and examined the resulting variations in the structural and electronic properties of the junctions.

2. SUMMARY OF THE MOST IMPORTANT RESULTS

Much of our work has been focussed on heterovalent semiconductor heterojunctions, i.e. heterostructures and superlattices comprised of materials with different chemical valence (e.g. II-VI/III-V or III-V/IV). Heterovalent semiconductor heterojunctions are becoming increasingly important for the development of future optoelectronic devices, and offer promise to be the most easily tunable class of semiconductor heterojunctions. This is because ideally abrupt heterovalent heterojunctions with polar orientation would be thermodynamically unstable, so that different interface reconstruction may develop to lead to neutral interfaces. The resulting different interface configurations may lead to widely different heterojunction parameters.

Our approach has been to use the growth parameters to kinetically favor one or the other of the different interface configurations, and modify the band discontinuities. The direction in which we have attempted to drive the interface reconstruction has been generally suggested by the results of first principle calculations of the band discontinuities as a function of the interface atomic configuration. The growth parameters at our disposal were those controllable during molecular beam epitaxy (MBE), namely the atomic or molecular fluxes of the elemental constituents, temperature, and substrate orientation. All heterostructures examined were therefore synthesized by MBE, and characterized in-situ by reflection high energy electron diffraction and photoemission spectroscopy, and ex-situ by x-ray diffraction, and transmission electron microscopy (TEM). In general, we determined by photoemission spectroscopy the composition profile achieved at the interface, the band discontinuities, and the charged versus neutral character of the interfaces.

We targeted a family of II-VI/III-V which include strained ZnSe/GaAs heterostructures as well as lattice-matched $\text{Zn}_{1-x}\text{Cd}_x\text{Se}/\text{In}_y\text{Ga}_{1-y}\text{As}$ heterostructures, which are crucial components of new optoelectronic devices operating in the blue region of the visible spectrum. For such heterojunctions, the large value reported for the valence band offset hinders hole injection in the active region for LEDs and lasers. However, first principle calculations suggest that a 1-eV wide range of band offsets might be achieved by varying the local atomic configuration at the interface. Experimentally we found that the Zn/Se beam pressure ratio (BPR) employed in the early stage of MBE fabrication of the heterostructure determines the local composition of the interface. High BPRs produce a Zn-rich interface composition, while low BPRs yield a Se-rich interface composition. The excess Zn or Se at the interface is of the order of one monolayer. Using synchrotron radiation photoemission spectroscopy for enhanced sensitivity we found that high Zn/Se flux ratios during the early stages of growth give rise to relatively abrupt interfaces, with little evidence of atomic intermixing, and an apparently Zn-rich Zn/Se relative composition.

Correspondingly, valence band offsets as high as 1.32-1.34eV were observed. Conversely, low Zn/Se flux ratios lead to enhanced atomic intermixing, with evidence of Ga-Se and As-Se bond formation, Ga outdiffusion in the overlayer and As surface segregation. The apparently Se-rich Zn/Se relative composition was accompanied by valence band offsets as low as 0.48-0.55eV. Such a wide range of tunability of the interface parameters is totally unprecedented, and could be exploited to substantially increase hole collection efficiency in blue LEDs and lasers.

Tuning the band alignment to optimize hole injection could have a substantial impact on device performance, but unfortunately comes at a price. The BPR employed controls also the optical properties of the ZnSe layer, and minimum incorporation of extended and point defects, as well as unintentional dopants is found in samples fabricated with near-stoichiometric growth conditions ($BPR \sim 1$). Lowest densities of stacking faults are observed for Zn-rich growth conditions ($BPR > 1$). Fabricating Se-rich interfaces requires BPR's much lower (~ 0.1) than those necessary to optimize such properties. We developed, however, a promising solution to this problem. We exploited the local character of the parameters that control the band offset and confine non-stoichiometric growth to a thin composition-control interface layer (CIL). We showed 2nm-thick CILs are sufficient to set the desired value of the band offsets, and that the band alignment does not change during the following growth stages in near-stoichiometric conditions. We used optical transmission measurements, complemented by photoluminescence studies, to demonstrate that the optical properties of CIL-incorporating heterostructures were dramatically improved as compared to those of structures fabricated in non-stoichiometric conditions.

We also conducted a series of studies on the stability of such engineered heterojunctions, in collaboration with colleagues at Xerox Corporation. ZnSe-GaAs heterojunctions were probed for deep level emission as a function of temperature by means of photoluminescence and cathodoluminescence spectroscopy. A series of previously unreported deep levels at 0.8, 0.98, 1.14, and 1.3 eV were identified which are characteristic of the ZnSe overlayer, and relatively independent in energy of overlayer thickness. These levels lie far below those of the near-band-edge features commonly used to characterize the ZnSe crystal quality. The relative intensity and spatial distribution of the deep level emission was found to be strongly affected by the BPR employed during ZnSe growth. In heterostructures fabricated in Se-rich growth conditions, that minimize the valence band offset and the concentration of Se vacancies, the dominant deep level emission is at 1.3 eV. For heterostructures fabricated in Zn-rich growth conditions, emission by multiple levels at 0.88, 0.98, and 1.14 eV dominates. Additional deep levels at 1.9-2.0eV appear related to thermal degradation of the interface and interdiffusion. The spectral energies and intensities of these deep level transitions might provide a new and improved characteristic indicator of ZnSe epilayer stoichiometry and near-interface defect densities.

The above in-situ studies were complemented by transport studies in which interfaces with different compositions were incorporated in functional n-ZnSe/p-GaAs heterojunction diodes. The goal of this second type of study was twofold. First, to gauge directly the effect of the local interface composition on the conduction-band offset. Second, to verify if engineered band offsets are observable in a complete device, having survived the following stages of device fabrication and processing. We designed heterostructures in which carriers could be photogenerated only in a 10nm-thick GaAs layer near the interface to avoid field induced transfer into GaAs satellite valleys before tunneling. From the systematics of the low-temperature current-voltage (I-V) spectra, and of the corresponding tunneling current, we deduced conduction band-offset values in remarkable agreement with those measured by electron spectroscopy in the thin-overlayer samples. This suggests that the metastable interface configurations responsible for band offset tuning in the thin overlayer samples are sufficiently stable to sustain the following stages of device fabrication and processing. Engineered band offsets can therefore be observed and exploited in practical devices. This was, to our knowledge, the first verification of a locally engineered heterojunction band offset in a fully functional device by transport methods. The only previous instance we are aware of dates back to the seminal work by Capasso et al. who used, however, doping-related dipoles as opposed to local modifications of the atomic configuration of the interface.

Our understanding of wide-gap II-VI semiconductor heterostructures lead us to develop a new method to obtain low-resistance metal/n-ZnSe contacts through fabrication of a Cl-doped graded n-Zn_{1-x}Cd_xSe interface layer. Our interest in the effect of Zn_{1-x}Cd_xSe interfacial layers on the properties of Al/n⁺-ZnSe junctions was stimulated by three main considerations: 1) The ternary alloy Zn_{1-x}Cd_xSe can be grown epitaxially on ZnSe by MBE and exhibits a bandgap which decreases monotonically with increasing Cd concentration x; 2) Recent studies indicate that the conduction band discontinuity accounts for most (70-80%) of the Zn_{1-x}Cd_xSe/ZnSe bandgap difference; and 3) Among the technologically relevant metals, aluminum is known to exhibit one of the lowest Schottky barriers to n-type ZnSe. We first performed SXPS studies of Al/Zn_{1-x}Cd_xSe Schottky barriers fabricated in ultra-high-vacuum conditions. We found that the p-type Schottky barrier varies only slightly with x, and that most of the bandgap variation in the alloy series is reflected by the parallel variation in the n-type barrier. We then performed I-V measurements on a number of Al/n-Zn_{1-x}Cd_xSe contacts fabricated with standard photolithographic techniques and found that the specific contact resistivity decreased monotonically with increasing Cd concentration and doping level. The lowest contact resistance observed in the presence of the ternary interface layer ($1.5 \pm 0.5 \times 10^{-5} \Omega \cdot \text{cm}^2$) was, to our knowledge, the lowest ever reported for a n-type ZnSe-based, wide gap semiconductor.

We pursued the elimination of the single remaining region of high strain in current II-VI based blue-green lasers, i.e., the lasing medium. Most lasers include Zn_{1-x}Cd_xSe quantum wells with x=0.25 (blue-green emitters) or x=0.15 (blue emitters) as optically active materials. The deeper quantum wells (x=0.25) exhibit a better temperature-dependence of the current threshold, but shorter low-temperature device lifetime. This has been related to the substantial compressive strain existing in the quantum wells (about 1.3% for y=0.15 and 1.9% for y=0.25 in pseudomorphic wells) which would assist defect formation and propagation. Strain in the quantum well is mandated by the lattice mismatch of the ternary active layers with both ZnSe and GaAs substrates. It could be eliminated, provided that suitable substrates lattice-matched to the ternary alloy wells are developed, since the remaining components of the device - namely the cladding and waveguiding alloy layers - can be easily grown lattice-matched to the active layers rather than to GaAs. For appropriate value of the In concentration y, In_yGa_{1-y}As alloys can be designed to match the lattice parameter of ZnSe or that of the Zn_{1-x}Cd_xSe active layers in blue or blue-green lasers. However, high quality In_yGa_{1-y}As wafers with x \geq 0.04 are not available, because of homogeneity problems in high-x bulk single crystals, and growth of In_yGa_{1-y}As buffer layers with optimized concentration and strain relaxation profile on GaAs seems the most promising option.

We focused on Zn_{1-x}Cd_xSe/In_yGa_{1-y}As/GaAs(001) heterostructures which included In_yGa_{1-y}As epilayers with homogeneous composition y=0, 0.18 and 0.27 as well as graded-composition layers in which x was gradually varied from x=0 to x_s=0.05, 0.23 and 0.33. The ternary buffer layers were designed to obtain in-plane surface lattice constant matching that of Zn_{1-x}Cd_xSe with x=0, 0.15 and 0.25. On such substrates, dislocation-free growth of thick Zn_{1-x}Cd_xSe films was readily achieved both on homogenous-composition as well as on graded-composition buffers in which the indium concentration was varied a superlinear, parabolic profile. The more complex, graded-composition profile was found to retard the nucleation of new dislocations due to the grading of the strain and reduces dislocation interaction, since the dislocations are distributed throughout the graded volume, and this leads to lower threading dislocation densities in both the III-V buffer and the II-VI active layer. Photoluminescence studies indicated an improvement of over two orders of magnitude in the ratio of the near-band-edge versus defect-related emission as a result of the presence of the ternary buffer.

Progress in eliminating dislocations and strain from the laser structure may reduce but not eliminate the problem of early laser degradation, so that attention has also been focused on other types of native defects which are preferentially located at the II-VI/III-V interface and may contribute to device degradation. In particular, degradation during cw operation of pseudomorphic laser structures at room temperature has been associated with stacking faults at the II-VI/III-V interface. Such defects would propagate through the structure during growth and generate dislocation sources within the strained Zn_{1-x}Cd_xSe active layers. The existence of relatively high densities of native stacking faults at II-VI/III-V interfaces has been known for some time and tentatively explained by mechanisms as different as island coalescence during II-VI epilayer

growth, doping, or substrate roughness. Both intrinsic and extrinsic stacking faults, which are formed by removing or inserting, respectively, a portion of a closed-packed {111} plane have been reported, in pairs or as isolated defects, starting in all cases at or near the II-VI/III-V interface and propagating throughout the II-VI epilayer, bounded by Frank or Shockley partial dislocations.

We found evidence that the Zn/Se flux ratio employed during the early stages of ZnSe growth by MBE on GaAs as well as $\text{In}_y\text{Ga}_{1-y}\text{As}$ surfaces has a profound effect on the resulting density of native stacking faults. We found that the use of low Zn/Se BPRs, i.e., Se-rich growth conditions, during interface fabrication yields stacking fault densities dramatically lower than those obtained with high Zn/Se BPRs. Since we had shown earlier that the BPR controls the interface composition and the band alignment, the present results indicate that the local atomic configuration of the interface contributes to determine the probability of stacking fault nucleation.

3. COMPREHENSIVE PUBLICATION LIST

- 3.1 G. Bratina, L. Sorba, A. Antonini, G. Ceccone, R. Nicolini, G. Biasiol, A. Franciosi, J.E. Angelo, and W.W. Gerberich, "Band Offsets and Strain in CdTe-GaAs Heterostructures", *Phys. Rev. B* **48**, 8899 (1993).
- 3.2 J.E. Angelo, W.W. Gerberich, G. Bratina, L. Sorba, and A. Franciosi, "Effects of Surface Reconstruction on CdTe/GaAs(001) Interface Structure", *J. Cryst. Growth* **130**, 459 (1993).
- 3.3 J.E. Angelo, W.W. Gerberich, W.M. Stobbs, G. Bratina, L. Sorba, and A. Franciosi, "The Coherency Loss Microstructure at a CdTe/GaAs(001) Interface", *Phil. Mag. Lett.* **67**, 279 (1993).
- 3.4 A. Franciosi, L. Sorba, G. Bratina, and G. Biasiol, "Modification of Heterojunction Band Offsets at III-V/IV/III-V Interfaces", *J. Vac. Sci. Technol. B* **11**, 1628 (1993).
- 3.5 A. Franciosi, L. Sorba, G. Bratina, L. Vanzetti, Guido Mula, G. Biasiol, and R. Nicolini, "Novel Materials for Optoelectronics", *Alta Frequenza (Italy)* **5**, 214 (1993).
- 3.6 R. Nicolini, L. Vanzetti, Guido Mula, G. Bratina, L. Sorba, A. Franciosi, M. Peressi, S. Baroni, R. Resta, A. Baldereschi, J.E. Angelo, and W.W. Gerberich, "Local Interface Composition and Band Discontinuities in Heterovalent Heterostructures", *Phys. Rev. Lett.* **72**, 294 (1994).
- 3.7 J.E. Angelo, W.W. Gerberich, G. Bratina, L. Sorba, and A. Franciosi, M.J. Mills, "TEM Investigation of CdTe(111)/GaAs(001) Interfaces", *MRS Proceedings* **319**, 129 (1994).
- 3.8 L. Sorba, G. Bratina, G. Biasiol, and A. Franciosi, "Microscopic Control of Band Offsets in Semiconductor Heterostructures", in: *Formation of Semiconductor Interfaces*, B. Lengeler, H. Lüth, W. Mönch, and J. Pollmann, eds. (World Scientific, Singapore, 1994), pp. 589-596.
- 3.9 T. dell'Orto, J. Almeida, C. Coluzza, A. Baldereschi, G. Margaritondo, M. Cantile, S. Yildirim, L. Sorba and A. Franciosi, "Internal Photoemission Studies of Artificial Band Discontinuities at Buried GaAs(100)/GaAs(100) Homojunctions", *Appl. Phys. Lett.* **64**, 2111 (1994).
- 3.10 R. Cingolani, R. Rinaldi, L. Calcagnile, P. Prete, P. Sciacovelli, L. Tapfer, L. Vanzetti, Guido Mula, F. Bassani, L. Sorba, and A. Franciosi, "Recombination Mechanisms and Lasing in Shallow $\text{Zn}_{0.9}\text{Cd}_{0.1}\text{Se/ZnSe}$ Quantum Well Structures", *Phys. Rev. B* **49**, 16769 (1994).
- 3.11 R. Nicolini, L. Vanzetti, Guido Mula, G. Bratina, L. Sorba, A. Mura, J.E. Angelo, W.W. Gerberich, and A. Franciosi, "Local Interface Composition and Band Offset Tuning in ZnSe-GaAs(001) Heterostructures", *MRS Proceedings* **326**, 3 (1994).

- 3.12 G. Bratina, L. Vanzetti, L. Sorba, G. Biasiol, A. Franciosi, M. Peressi, and S. Baroni, "Lack of Band Offset Transitivity for Semiconductor Heterojunctions with Polar Orientations: ZnSe-Ge(001), Ge-GaAs(001), and ZnSe-GaAs(001)", *Phys. Rev. B* **50**, 11723 (1994).
- 3.13 R. Cingolani, M. Di Dio, M. Lomascolo, R. Rinaldi, P. Prete, L. Vasanelli, L. Vanzetti, Franck Bassani, A. Bonanni, L. Sorba, and A. Franciosi, "Photocurrent Spectroscopy of $\text{Zn}_{1-x}\text{Cd}_x\text{Se}/\text{ZnSe}$ Quantum Wells in p-i-n Heterostructures", *Phys. Rev. B* **50**, 12179 (1994).
- 3.14 A. Franciosi, L. Vanzetti, A. Bonanni, L. Sorba, G. Bratina, and G. Biasiol, "Interfacial Engineering in Blue Laser Structures", in *II-VI Blue/Green Laser Diodes*, R.L. Gunshor and A.V. Nurmikko, Eds., *Proc. SPIE* **2346**, 100 (1994).
- 3.15 G. Bratina, G. Biasiol, L. Vanzetti, A. Bonanni, L. Sorba, and A. Franciosi, "Nanosize Stress Concentrators at Facets in $\text{Zn}_{1-x}\text{Cd}_x\text{Se}/\text{ZnSe}$ Multiple Quantum Well Laser Structures", in *II-VI Blue/Green Laser Diodes*, R.L. Gunshor and A.V. Nurmikko, Eds., *Proc. SPIE* **2346**, 180 (1994).
- 3.16 A. Raisanen, L.J. Brillson, A. Franciosi, R. Nicolini, L. Vanzetti, and L. Sorba, "Deep Level Electronic Structure of ZnSe/GaAs Heterostructures", *J. Electron. Mater.* **24**, 163 (1995).
- 3.17 A. Bonanni, L. Vanzetti, L. Sorba, A. Franciosi, M. Lomascolo, P. Prete, and R. Cingolani, "Optimization of Interface Parameters and Bulk Properties in ZnSe-GaAs Heterostructures", *Appl. Phys. Lett.* **66**, 1092 (1995).
- 3.18 L. Vanzetti, A. Bonanni, L. Sorba, A. Franciosi, M. Lomascolo, D. Greco, and R. Cingolani, "Heterovalent Semiconductor Heterostructures: Local Versus Bulk Properties", in *Proceedings 22th Int. Conf. on the Physics of Semiconductors*, D.J. Lockwood, Ed. (World Scientific, Singapore, 1995), 767-770.
- 3.19 L. Calcagnile, M. Di Dio, M. Lomascolo, R. Rinaldi, P. Prete, R. Cingolani, L. Vanzetti, A. Bonanni, Franck Bassani, L. Sorba, and A. Franciosi, "Recombination Mechanisms in Photopumped $\text{Zn}_{1-x}\text{Cd}_x\text{Se}/\text{ZnSe}$ Multiple Quantum Well Lasers", *J. Cryst. Growth* **150**, 712 (1995).
- 3.20 L. Vanzetti, A. Bonanni, G. Bratina, L. Sorba, A. Franciosi, M. Lomascolo, D. Greco, and R. Cingolani, "Influence of Growth Parameters on the Properties of ZnSe/GaAs(001) Heterostructures", *J. Cryst. Growth* **150**, 765 (1995).
- 3.21 A. Franciosi, L. Vanzetti, L. Sorba, A. Bonanni, R. Cingolani, M. Lomascolo, and D. Greco, "Band Offset Engineering of II-VI/III-V Heterostructures", *Mater. Sci. Forum* **182-184**, 17 (1995).
- 3.22 A. Raisanen, L.J. Brillson, L. Vanzetti, L. Sorba, and A. Franciosi, "Deep Levels Near "Buried" ZnSe/GaAs(100) Heterointerfaces", *J. Vac. Sci. Technol. A* **13**, 690 (1995).
- 3.23 A. Raisanen, L.J. Brillson, L. Vanzetti, L. Sorba, and A. Franciosi, "Atomic Diffusion-induced Deep Levels near ZnSe/GaAs(100) Interfaces", *Appl. Phys. Lett.* **66**, 3301 (1995).
- 3.24 A. Raisanen, L.J. Brillson, L. Vanzetti, A. Bonanni, and A. Franciosi, "Deep Level Formation at ZnSe/GaAs(100) Interfaces", *J. Vac. Sci. Technol. B* **13**, 1705 (1995).

- 3.25 I. Karpov, N. Venkateswaran, G. Bratina, W. Gladfelter, A. Franciosi, and L. Sorba, "Arsenic Cap Layer Desorption and the Formation of GaAs(100) c(4x4) Surfaces", *J. Vac. Sci. Technol. B* **13**, 2041 (1995).
- 3.26 G. Bratina, L. Vanzetti, and A. Franciosi, "Cross-sectional Lateral-force Microscopy of Semiconductor Heterostructures and Multiple Quantum Wells", *Phys. Rev. B* **52**, R8625 (1995).
- 3.27 M. Lazzarino, T. Ozzello, G. Bratina, L. Sorba, and A. Franciosi, "Low Resistance Graded Contacts to n-type ZnSe", *Appl. Phys. Lett.* **68**, 370 (1996).
- 3.28 Y. Fan, I. Karpov, G. Bratina, L. Sorba, W. Gladfelter, and A. Franciosi, "Atomic Scale Roughness of GaAs(001)2x4 Surfaces", *J. Vac. Sci. Technol. B* **14**, 623 (1996).
- 3.29 M. Lazzarino, T. Ozzello, G. Bratina, L. Vanzetti, J.J. Paggel, L. Sorba, and A. Franciosi, "Improved Contact Resistance to n-type Wide Gap II-VI Semiconductors", *J. Cryst. Growth.* **159**, 718 (1996).
- 3.30 G. Bratina, L. Vanzetti, A. Bonanni, L. Sorba, J.J. Paggel, A. Franciosi, T. Peluso, and L. Tapfer, "Structural Properties of ZnSe/GaAs(100) Heterostructures with Engineered Band Offsets", *J. Cryst. Growth* **159**, 703 (1996).
- 3.31 G. Bratina, T. Ozzello, and A. Franciosi, "Interfacial Chemical Bonds, Reactions, and Band Alignment in ZnSe-GaAs(001) Heterojunctions", *J. Vac. Sci. Technol. B* **14**, 2967 (1996).
- 3.32 S. Heun, J.J. Paggel, S. Rubini, and A. Franciosi, "Zn Preadsorption on GaAs(100)2x4 Prior to ZnSe Growth", *J. Vac. Sci. Technol. B* **14**, 2980 (1996).
- 3.33 M. Lazzarino, T. Ozzello, G. Bratina, L. Sorba, and A. Franciosi, "Low Resistance Graded Contacts to n-type ZnSe", *Appl. Phys. Lett.* **68**, 370 (1996).
- 3.34 V. Pellegrini, M. Börger, M. Lazzeri, F. Beltram, J.J. Paggel, L. Sorba, S. Rubini, M. Lazzarino, A. Franciosi, J.-M. Bonard, and J.-D. Ganiere, "Tuning of ZnSe-GaAs Band Discontinuities in Heterojunction Diodes", *Appl. Phys. Lett.* **69**, 3233 (1996).
- 3.35 L. Sorba, J.J. Paggel, and A. Franciosi, "Tunable Schottky Barriers and the Nature of Si Interface Layers in Al/GaAs(001) Diodes", *J. Vac. Sci. Technol. B* **14**, 2994 (1996).
- 3.36 X. Yang, L.J. Brillson, A.D. Raisanen, L. Vanzetti, A. Bonanni, and A. Franciosi, "Internal Photoinjection and Deep Level Luminescence at ZnSe/GaAs Heterointerfaces", *J. Vac. Sci. Technol. A* **14**, 867 (1996).
- 3.37 G. Bratina, T. Ozzello, and A. Franciosi, "Chemical Bonding and Electronic Properties of Se-rich ZnSe-GaAs(001) Interfaces", *J. Vac. Sci. Technol. A* **14**, 3135 (1996).
- 3.38 A. Franciosi and C.G. Van de Walle, "Heterojunction Band Offset Engineering", *Surf. Sci. Rep.* **25**, 1 (1996).
- 3.39 X. Yang, L.J. Brillson, A.D. Raisanen, L. Vanzetti, A. Bonanni, A. Franciosi, M. Grundmann, and D. Bimberg, "Evolution of Deep Levels and Internal Photoemission with Annealing Temperature at ZnSe/GaAs Interfaces", *J. Vac. Sci. Technol. B* **14**, 2961 (1996).
- 3.40 S. Heun, J.J. Paggel, S. Rubini, L. Sorba, A. Franciosi, J.-M. Bonard, and J.-D. Ganiere, "Interface Composition and Stacking Fault Density in II-VI/III-V Heterostructures", *Appl. Phys. Lett.* **70**, 237 (1997).

- 3.41 S. Heun, J.J. Paggel, L. Sorba, S. Rubini, A. Franciosi, J.-M. Bonard, and J.-D. Ganiere, "Local interface composition and extended defect density in ZnSe/GaAs and ZnSe/In_{0.04}Ga_{0.96}As (001) heterojunctions", J. Vac. Sci. Technol. B **15**, 1279 (1997).

3. REPORTABLE INVENTIONS

None.

4. PARTICIPATING SCIENTIFIC PERSONNEL SUPPORTED

- 2.1 G. Bratina, Research Associate
- 2.2 D. Cohen, Research Assistant
- 2.3 D. Coldwell, Research Assistant
- 2.4 A. Franciosi, Associate Professor